

Technical Data Sheet

EG1356-90063

Laqva Top 30

Product description

One component waterborne topcoat aimed for use for furniture and interior joinery. Both solid wood and MDF is suitable as substrate. It is fast drying has good stackability both after forced drying by IRM and jet air as well at low temperature drying and gives good scratch resistance. Other benefits are excellent adhesion to UV primers and waterborne primers.

Product data

Gloss:	29-33	Gardner 60°	
Solid content:	46 ±1	[weight %] theoretical	
Specific gravity:	1210 ±30	[kg/m ³]	
Viscosity:	84-90	[KU] Stormer	test performed at 23 °C
Flammable:	No	Flash point > 55°C	
Frost sensitive:	Yes		
Storing:	6 months	At 5-30 °C	Storing at higher temperature reduces shelf life, do not expose to direct sunlight

Mixing/Application

Recommended application method	Hardener	Amount hardener [Parts by vol]	Dilutant	Application viscosity	Application amount [g/m ²]	Notes
Air less spraying			Water	Delivered	90-120	
Air mix spraying			water	Delivered	90-120	
Stir well before use!						
Cleaning:	XX699					
	Water					

Drying

Method	Drying condition	Drying time	Notes
Jet air	50 °C	5-8 min	Depends on amount
Air Drying	20 °C	15-20 min	Depends on amount

All kind of drying requires good ventilation and circulation

Do not stack before surface temperature below 30 °C

Exterior products: should not be exposed to water, water condensation or temperatures below 0 °C with in 48 h after application

Curing

UV-dose	Min UV dose [mJ/cm ²]	Rec min Peak. [mW/cm ²]	Min UV dose [mJ/cm ²]	Rec min Peak. [mW/cm ²]
	Hg lamps (280-320 nm)	Hg	Ga lamps (390-450 nm)	Ga
Full cure	N/A			
Semi cure	N/A			

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

General information

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: 2014-02-28 (Valid 1 year from issue date)

Latest update: 120430