## **BotaGreen GreenHero**

Multifunctional tile adhesive C2 TE S1

# Botament



BotaGreen GreenHero is a multifuctional light-weight tile adhesive for the fitting of almost all ceramic wall and floor coverings and natural stones which are non-sensitive to discolouration in interior and exterior areas and on heated areas.

Because of the climate-friendly and resource-saving binder technology, approx. 30% CO<sub>2</sub> is saved during production\*.

Due to the Air-flow-technology BotaGreen GreenHero is particularly easy and smooth to handle.

PROPERTIES	<ul> <li>Heroic handling</li> <li>4 Superpowers in 1**</li> <li>Fastest of his guild***</li> <li>~ 30% CO<sub>2</sub> saving</li> <li>Dust-reduced</li> <li>Very low emission</li> <li>Very productive multifunctional tile adhesive C2 TE S1</li> <li>Especially suitable for large formats</li> <li>For heated areas, balconies and terraces</li> <li>Especially stable according to EN12004</li> <li>Filling up to 20 mm in one working step</li> <li>Long open time</li> <li>Crystalline water bonding</li> <li>certificated as a system in connection with the BotaGreen AE Sealing and decoupling membrane</li> </ul>
AREAS OF APPLICATION	<ul> <li>Bonding of</li> <li>vitreous stoneware and porcelain stoneware</li> <li>non-vitreous stoneware</li> <li>split tiles</li> <li>floor clinker slabs and clinker tiles</li> <li>hand-made tiles</li> <li>small and medium-sized mosaics</li> <li>natural stones which are non-sensitive to discolouration</li> <li>insulation and lightweight building boards</li> <li>Very smooth boards (e.g. rigid foam slabs) must be roughened up prior to bonding.</li> </ul>
SUITABLE SUBSTRATES	<ul> <li>concrete, lightweight concrete and porous concrete</li> <li>joint full brickwork</li> <li>plasters of the mortar categories CS II, CS III and CS IV in accordance with EN 998 (compressive strength ≥ 1.5 N/mm<sup>2</sup>) and gypsum plaster in accordance with EN 13279 (compressive strength ≥ 2.0 N/mm<sup>2</sup>)</li> <li>Botament BP building boards</li> <li>old tiling</li> <li>gypsum walls, gypsum plaster boards and gypsum fibreboards</li> <li>cement screeds and calcium sulphate screeds</li> <li>sanded mastic asphalt screeds (IC 10)</li> </ul>

Application on porous concrete and mastic asphalt screeds is only permissible in interior areas.

- dry, clean and frost-free
- stable
- free from grease, paint, cement laitance, separating agents, sinter layers and loose particles
- in true alignment and perpendicular

#### Please also note:

- unevenness of wall and floor surfaces are to be levelled with M200 Multi-mortar
- carry out large surface floor levelling with levelling compounds M50 Classic, M51 Classic or M53 Extra
- absorbent substrates must be primed with D1 Speed or D11
- prime calcium sulphate screeds with D11 (2 x undiluted), G140 or E120 (scatter G140 and E120 with quartz sand while fresh)
- where the substrate is gypsum → minimum layer: 10 mm, surface condition: rough, not felted or smoothed
- perform a Concrete Moisture Test to check the residual moisture in cement and calcium sulphate screeds

#### maximum permissible residual moisture

substrate	unheated	heated
cement screed	2.0- 2.5 %	2.0- 2.5 %
calcium sulphate screed	0.5 %	0.3 %

- minimum age of concrete substrates: 3 months
- maximum layer thickness of BotaGreen GreenHero on sanded mastic asphalt screeds: 5 mm

Gypsum plasters must be dried out. If the substrate is made from non-absorbent material or is made of old tiles, it must first be primed using D1 Speed (undiluted) or must receive a scratch coat made of Bota-Green GreenHero 24 hours prior to installation using.

**APPLICATION** 

CONSUMPTION

- mix up using cold, clean water while stirring with a slow rotating agitator until a homogenous, stiff and paste-like mass has formed
- briefly stir again after the maturing time first apply a thin contact layer of BotaGreen GreenHero using the smooth side of the notched trowel onto the substrate
- then apply BotaGreen GreenHero onto the fresh contact layer with the notched side of the trowel
- press tiles using light pressure and a side-to-side movement into the adhesive bed and position

thin-bed		
6 mm notched trowel	$\sim$ 1.6 kg/m <sup>2</sup>	
8 mm notched trowel	~ 2.1 kg/m²	
10 mm notched trowel	$\sim$ 2.6 kg/m²	
medium-bed	$\sim 3.1~{ m kg/m^2}$	
pourable bed		
8 mm notched trowel	$\sim 1.9~{ m kg/m^2}$	
10 mm notched trowel	$\sim 2.4~{ m kg/m^2}$	

#### **IMPORTANT ADVISORIES**

\* By using a climate-friendly binder with latent hydraulic components, approx. 30% CO<sub>2</sub> is saved in cement production. This figure refers to a Botament tile adhesive with comparable properties.

\*\*can be used as a thin, medium and pourable bed adhesive as well as a filler up to a layer thickness of 20 mm

\*\*\*related to the BotaGreen tile adhesives

When installing ceramic coverings all existing standards and guidelines in their current versions must be observed.

For the application of tiles and slabs in in permanent wet areas such as swimming pools or wellness facilities, we recommend the use of M21 Classic, M21 HP or EKF500.

You can view or download the safety datasheet at www.botament.com.

To achieve optimal results we recommend conducting a site-specific test sample prior to using.

When fitting larger tiles (especially in connection with heated constructions) and for works in exterior areas, we recommend the use of BotaGreen GreenHero in the combined method or the use of a pourable bed adhesive from our product range.

When bonding insulation boards the current regulations must be observed.

If the substrate is made of gypsum-containing material, the respective manufacturer's guidelines must be observed.

BotaGreen GreenHero is certificated as a system in connection with the AE Sealing and Decoupling Membrane.

### **TECHNICAL VALUES & PRODUCT CHARACTERISTICS**

Characteristic	Unit	Value	Comments		
Density	kg/dm³	~ 1.3			
Thermal resistance	°C				
		< 80			
Optimum water solids content	%				
Thin-bed		~ 34			
Mid-bed		~ 30			
Pourable bed		~ 40			
Filler		~ 26			
Mixing ratio	I		water/18 kg		
Thin-bed		~ 6.1			
Mid-bed		~ 5.4			
Pourable bed		~ 7.2			
Filler		~ 4.7			
Ageing time	minutes	~ 5			
Open time	minutes	~ 30			
Working time	hours	~ 3 - 4			
Adhesive bed thickness	mm	≤ 20			
Accessible after	hours	~ 12			
Groutable after	hours	~ 12			
Resilient after (full)	days	~ 7			
Application conditions	°C	> 5 < 30			
	All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.				
base	cement combination with mineral lightweight-fillers and additives				
delivery form	18 kg bag				
Storage	Can be stored in cool and dry conditions for at least 12 months in original unopened packs.Store in a cool, dry place!				
GISCODE	ZP 1				
Cleaning agent	when fresh: water, when fully cured: cement laitance remover				

**Note:** The information contained in this data sheet is based on our experience and is correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual structure, to the specific application and to non-standard local conditions. Application-specific conditions must be checked in advance by the planning engineer/specifier and, where different from the standard conditions indicated, will require individual approval. Technical advice provided by MC's specialist consultants does not replace the need for a planning review by the client or its agents in respect of the history of the building or structure. Subject to this prerequisite, we are liable for the correctness of this information within the framework of our terms and conditions of sale and delivery. Recommendations of our employees deviating from the information given in our data sheets are only binding for us if they are confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be observed. The information given in this technical data sheet is valid for the product supplied by the country company listed in the footer. It should be noted that data in other countries may differ. The product data sheets valid for the relevant foreign country must be observed. The latest technical data sheet shall apply to the exclusion of previous, duly superseded versions; the date of issue in the footer must be observed. The latest version is available from us on request or may be downloaded from our website. [2300013527]